

Espumas recicladas

Interplasp

Grado	Densidad			Dureza				
20S	20,0	±	1,60	kg/m ³	1,7	±	0,26	kPa·s
20D	20,0	±	1,60	kg/m ³	3,6	±	0,54	kPa·s
21M	21,0	±	1,68	kg/m ³	3,6	±	0,54	kPa·s
23S	23,0	±	1,84	kg/m ³	3,0	±	0,45	kPa·s
23D	23,0	±	1,84	kg/m ³	4,0	±	0,60	kPa·s
25RT	25,0	±	2,00	kg/m ³	2,8	±	0,42	kPa·s
25S	25,0	±	2,00	kg/m ³	3,3	±	0,50	kPa·s
25D	25,0	±	2,00	kg/m ³	4,2	±	0,63	kPa·s
26DX	26,0	±	2,08	kg/m ³	3,6	±	0,54	kPa·s
26HD	26,0	±	2,08	kg/m ³	7,0	±	1,05	kPa·s
28SSGM	28,0	±	2,24	kg/m ³	2,8	±	0,42	kPa·s
28S	28,0	±	2,24	kg/m ³	3,6	±	0,54	kPa·s
28HD	28,0	±	2,24	kg/m ³	6,7	±	1,01	kPa·s
30PSV	30,0	±	2,40	kg/m ³	3,0	±	0,45	kPa·s
30XD	30,0	±	2,40	kg/m ³	8,0	±	1,20	kPa·s
30HD	30,0	±	2,40	kg/m ³	7,0	±	1,05	kPa·s
32S	32,0	±	2,56	kg/m ³	4,0	±	0,60	kPa·s
35SOJA	35,0	±	2,80	kg/m ³	3,3	±	0,50	kPa·s

Tolerances values are 8% for density and 15% for hardness (UNE-EN ISO 53967:2015)